

**Amendments to the Claims:**


This listing of claims will replace all prior versions and listings of claims in the application.

**Listing of Claims:**

1. (Currently Amended) A radiation-sensitive resin composition comprising:

(A) a resin which comprises from 5 to 90 mole percent of a recurring unit (I-1)

shown by the following formula (I-1):




wherein  $R_{1a}$  represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms,  $X_1$  and  $X_2$  individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms,  $l$  is an integer of 0-5, and  $n$  is an integer of 0-2, the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid, and


(B) a photoacid generator.

2. (Currently Amended) ~~The radiation-sensitive resin composition according to claim 1, wherein the resin further comprises~~ A radiation-sensitive resin composition comprising:

(A) a resin which comprises a recurring unit (1-1) shown by the following formula (I-1):



wherein  $R_{1a}$  represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms,  $X_1$  and  $X_2$  individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms,  $l$  is an integer of 0-5, and  $n$  is an integer of 0-2, and a recurring unit (1-2) shown by the following formula (I-2):



wherein  $\text{R}_{1b}$  represents a hydrogen atom or a methyl group,  $\text{R}_{1c}$  individually represents a monovalent alicyclic hydrocarbon group having 4-20 carbon atoms or a derivative thereof, or a linear or branched alkyl group having 1-4 carbon atoms, provided that (1) at least one of the  $\text{R}_{1c}$  groups is a monovalent alicyclic hydrocarbon group having 4-20 carbon atoms, or (2) any two of the  $\text{R}_{1c}$  groups form, in combination and together with the carbon atom with which these groups bond, a divalent alicyclic hydrocarbon group having 4-20 carbon atoms or a derivative thereof, with the other  $\text{R}_{1c}$  group being a monovalent alicyclic hydrocarbon group having 4-20 carbon atoms or a derivative thereof, or a linear or branched alkyl group having 1-4 carbon atoms the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid, and


(B) a photoacid generator.

3. (Original) The radiation sensitive resin composition according to claim 2, wherein the group  $-\text{C}(\text{R}_{1c})_3$  in the formula (I-2) is a 1-alkyl-1-cycloalkyl group, 2-alkyl-2-adamantyl group, (1-alkyl-1-adamantyl)alkyl group, or (1-alkyl-1-norbornyl)alkyl group.

4. (Original) The radiation-sensitive resin composition according to claim 1, wherein the resin does not contain a lactone ring.

5. (Currently Amended) ~~The radiation-sensitive resin composition according to claim 4,~~ A radiation-sensitive resin composition comprising:

(A) a resin which comprises from 5 to 90 mole percent of a recurring unit (1-1) shown by the following formula (I-1):



wherein  $R_{1a}$  represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms,  $X_1$  and  $X_2$  individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms, 1 is an integer of 0-5, and n is an integer of 0-2, the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid, and


(B) a photoacid generator,

wherein the resin does not contain a lactone ring, and


wherein the content of the recurring unit (1-1) in the resin is 40-90 mol% in 100 mol% of the total recurring units forming the resin.

6. (Currently Amended) ~~The radiation-sensitive resin composition according to claim 1, wherein the resin further comprises~~ A radiation-sensitive resin composition comprising:

(A) a resin which comprises a recurring unit (1-1) shown by the following formula (I-1):



wherein R<sub>1a</sub> represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms, X<sub>1</sub> and X<sub>2</sub> individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms, 1 is an integer of 0-5, and n is an integer of 0-2, and a recurring unit (1-3) shown by the following formula (I-3):




wherein  $R_{1b}$  represents a hydrogen atom or a methyl group, the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid, and

(B) a photoacid generator.


7. (Original) The radiation-sensitive resin composition according to claim 6, wherein the content of the recurring unit (1-1) in the resin is 5-25 mol% in 100 mol% of the total recurring units forming the resin.

8. (Currently Amended) ~~The radiation-sensitive resin composition according to claim 1, wherein the resin further comprises~~ A radiation-sensitive resin composition comprising:

(A) a resin which comprises a recurring unit (1-1) shown by the following formula (I-1):



wherein  $R_{1a}$  represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms,  $X_1$  and  $X_2$  individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms,  $l$  is an integer of 0-5, and  $n$  is an integer of 0-2, and a recurring unit (I-4) shown by the following formula (I-4):



wherein  $R_{1b}$  represents a hydrogen atom or a methyl group,  $A$  represents a linear or branched alkyl or alkylene group having 1-4 carbon atoms or a monovalent or divalent alicyclic hydrocarbon group having 4-20 carbon atoms or a derivative thereof, and  $n$  is an


integer of 0-2, the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid, and

(B) a photoacid generator.

9. (Original) The radiation-sensitive resin composition according to claim 1, further comprising (C) an acid diffusion controller.

10. (New) A radiation-sensitive resin composition comprising:

(A) a resin which comprises a recurring unit (1-1) shown by the following formula (I-1):



wherein  $R_{1a}$  represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms,  $X_1$  and  $X_2$  individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms, 1 is an integer of 0-5, and  $n$  is an integer of 0-2, the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid,




(B) a photoacid generator, and

(C) an acid diffusion controller.

11. (New) A radiation-sensitive resin composition comprising:

(A) a resin which comprises a recurring unit (1-1) shown by the following formula (1-1):



wherein  $R_{1a}$  represents a hydrogen atom, a methyl group, a hydroxyalkyl group having 1-4 carbon atoms, or a perfluoroalkyl group having 1-4 carbon atoms,  $X_1$  and  $X_2$  individually represent a hydrogen atom, a fluorine atom, an alkyl group having 1-4 carbon atoms, or a fluoroalkyl group having 1-4 carbon atoms,  $l$  is an integer of 0-5, and  $n$  is 1 or 2, the resin being insoluble or scarcely soluble in alkali, but becoming alkali soluble by the action of an acid, and

(B) a photoacid generator.

12. (New) The radiation-sensitive resin composition according to Claim 11, wherein  $n$  is 1,  $l$  is 1, each  $X_1$  is H and each  $X_2$  is  $CF_3$ .